

nyco[®] BLOCK FILLER

NYCO SUPPLIES PREMIUM QUALITY WOLLASTONITE TO THE WORLD

NYCO is not only the foremost supplier
of wollastonite in the world,
we are also the first...

Since our pioneering plant at Willsboro,
New York opened in 1953, to our most
recent development of a world class
deposit in the Sonora desert of Mexico,
NYCO has led the world in its growing
acceptance of wollastonite.

- highest quality ores
- state of the art processing
- world class treatment facilities
- market leading reliability
& technical service
- 100's of years of reserves

This data contains general information and describes
typical properties only. It is offered for use by
persons qualified to determine for themselves the
suitability of our products for particular purposes.
No guarantee is made or liability assumed, the
application of this data and the products described
herein being at the sole risk of the user.

For detailed information on NYAD G[®]
Wollastonite please contact **NYCO Minerals, Inc.**
(an ISO 9002 certified facility).

HEALTH & SAFETY STATEMENT: Wollastonite is a naturally
occurring, non-hazardous mineral. The benign health
aspect of wollastonite provides a compelling reason for its
use in place of other industrial minerals and fibers.

FORMULATION NO. E-1461

INGREDIENTS	POUNDS	GALLONS
PIGMENT GRIND		
Water	208.30	25.00
Phenyl Mercuric Acetate, 100%	0.25	-
Dispersant ⁽¹⁾	4.60	0.50
Potassium Tripolyphosphate (KTPP)	1.00	0.05
TERGITOL Nonionic Surfactant NP-10	2.20	0.25
Antifoam ⁽²⁾	0.90	0.13
Titanium Dioxide ⁽³⁾	50.00	1.45
Calcium Carbonate ⁽⁴⁾	500.00	22.15
GRIND 10 MINUTES, THEN ADD:		
Water	58.30	7.00
NYAD G [®] Wollastonite	100.00	4.13
LET DOWN		
UCAR Latex 376	262.50	29.00
PREMIX: Ethylene Glycol	18.60	2.00
CELLOSIZO Hydroxyethyl Cellulose QP-15 000	5.00	0.45
Water	54.20	6.51
Coalescing Aid ⁽⁵⁾	7.90	1.00
Antifoam	1.80	0.38
TOTAL	1275.60	100.00
A FIBROUS BLOCK FILLER WITH GOOD MUD CRACK RESISTANCE.		

SUPPLIERS

- 1) "Tamol" 731 (Rohm and Haas) or equivalent.
- 2) "Foamaster" SA-1 (Diamond Shamrock) or equivalent.
- 3) RCL-9 (Glidden) or equivalent.
- 4) "No. 1 White" (Thompson, Weinman) or equivalent.
- 5) "Texanol" (Eastman) or equivalent. For improved freeze/thaw stability, a more water-soluble coalescent, such as Butyl Carbitol, may be used.

NYCO Minerals, Inc.
P.O. Box 368, 803 Mountain View Dr.
Willsboro, NY, 12996-0368 USA
Tel: (518) 963-4262 Fax: (518) 963-1110

nyco[®]

PREMIUM QUALITY WOLLASTONITE

www.nycominerals.com

EUROPE
Belgium
Tel: (32) 10 88 13 02 Fax: (32) 10 22 65 99

MEXICO
Hermosillo, Sonora, Mexico
Tel: (52) 62 89 10 00 Fax: (52) 62 89 10 90